


GEL DEEP CYCLE SERIES

MODEL: JS200-12(GEL) 12V 200Ah 10HR



Plane Chart:



Package:





GEL DEEP CYCLE SERIES


MODEL: JS200-12(GEL) 12V 200Ah 10HR

Parameter Chart:


Volts			12V					
Capacity (25°C	5)		200Ah					
Discharge Curre	nt		110Ah					
Testing (25°C)			150Ah					
Internal Resistan	ice	Fu	3.2m Ω					
			104%					
Capacity Affects	Capacity Affected By Temperature		25°C					
By Temperatur			0°C					
			65%					
		Capa	91%					
Residual Capac (25°C)	Residual Capacity (25°C)		Capacity After 6 Months Storage					
			city After 12 Months Storage	65%				
Charge (constant	Сус	cle (25°C)	Initial Charging Less Than 6 Voltage 14.5 ~	60A				
voltage)	Flo	at (25°C)	Charge Voltage 13	3.6 ~ 13.8V				
	Weight (App	rox)	60.	2Kg				

[★] The above are average and data obtained from the first 3 charge/discharge cycles. These are not minimum values.

Residual Capacity



Discharge Current 25℃







GEL DEEP CYCLE SERIES

MODEL: JS200-12(GEL) 12V 200Ah 10HR

Constant voltage charging characteristics



Cycle service life in relation to the depth of discharge



Contstant Curent Discharge Characteristics (A,25°C)

F.V/Time	15min	30min	60min	2h	3h	4h	5h	8h	10h	20h
9.60V	366.3	207.9	128.7	72.4	54.5	41.4	37.8	24.1	20.1	10.2
10.2V	351.5	200.0	123.8	71.3	53.0	40.9	36.6	23.9	20.1	10.2
10.5V	344.5	195.0	120.8	70.7	52.6	40.6	36.3	23.8	20.0	10.1
10.8V	333.6	190.1	117.8	69.8	51.9	39.4	35.9	23.5	20.0	10.1

Contstant Power Discharge Characteristics (Watt, 35°C)

F.V/Time	15min	30min	60min	2h	3h	4h	5h	8h	10h	20h
9.60V	4022.4	2332.4	1467.2	837.5	632.6	487.1	439.6	285.1	239.6	122.8
10.2V	3861.0	2239.4	1410.8	824.7	622.7	481.1	432.6	283.1	238.5	121.8
10.5V	3782.8	2187.9	1376.1	817.7	617.8	477.2	428.7	282.2	237.6	120.8
10.8V	3686.0	2127.5	1338.5	807.8	610.8	463.3	424.7	278.2	236.8	120.8

Capacity Factors With Different Temperature

Battery	Туре	-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%

[★]The above are average and data obtained from the firsr 3 charge/discharge cycles. These are not minimum values.